



Joint venture between SGS and IMME Mongolia



SGS IMME MONGOLIA LLC

### INSPECTION REPORT

Company : Darkhan Metallurgical Plant  
Location: Tumurtei Terminal  
Date: 2025.1.6

Sample No:	Product weight	H <sub>2</sub> O	Fe	S	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	TiO <sub>2</sub>	P	
		ton	%	%	%	%	%	%	
TLot 4	1	1,020.30	1.34	58.77	1.72	1.82	5.37	0.17	0.01
	2	1,046.70	2.27	58.57	1.88	1.70	5.88	0.19	0.01
	3	1,169.60	0.97	59.68	1.90	1.59	5.33	0.16	0.02
	4								
	5								
<b>Average result*</b>		<b>3,236.60</b>	<b>1.51</b>	<b>59.03</b>	<b>1.84</b>	<b>1.70</b>	<b>5.52</b>	<b>0.17</b>	<b>0.01</b>

NOTE: \*Average result of all analytes is for summary of product weight.  
This result format of the inspection sample only for DMP's internal use only .

Signature:



SGS-IMME Mongolia LLC